



Cotton fiber -Laminated-

Description

Type: HGW 2082 s. DIN 7735

Density: 1.3 g/cm³


Thickness: between 1 mm. and 100 mm.

Other sizes and formats upon request.



Technical sheet

	Longitudinal	Transversal
Flexural strength:	1360 kp/cm ²	1290 kp/cm ²
Tensile strength :	800kp/cm ²	650 kp/cm ²
Impact strength:	30 kp/cm ²	30 kp/cm ²



Tlf.: 946 314 289 - | - Fax: 946 313 868
Barrio San Lorenzo s/n 48390 Bedia (Bizkaia)
Mail: apyasa@apyasa.com