



# Bakelite -Laminated-

## Generalities


**Type:** HP 2061 / 2067.5 según DIN 7735

**Thermal class:** "E" (120°C)



## Technical sheet

	Norm	Units	M6	M8
Flexural strength	ISO 178	MPa	140	135
Tensile strength	ISO 527	MPa	110	120
Compressive strength	ISO 604	MPa	130	200
Elasticity in flexure	ISO 178	MPa	7000	7000
Density	ISO 1183	g/cm <sup>3</sup>	1,3 - 1,4	1,3 - 1,4
Water absorption (thickness 3 mm)	ISO 62	mg.	260	550
Sizes	-	mm.	1040X1080	1600X3200
	-		1040X2240	1300X3200
	-			1300X2800
Thickness		mm.	1-100	0,4 - 30



Tlf.: 946 314 289 - | - Fax: 946 313 868  
Barrio San Lorenzo s/n 48390 Bedia (Bizkaia)  
Mail: [apyasa@apyasa.com](mailto:apyasa@apyasa.com)