



Crepe

Generalities

Type: P5328 según DIN 6740

Thermal class: "A" (105°C)

Formats:


Diámetro between 4 and 60 mm.
Max length without joint 1200 mm.
100 units packet supply, wrapped on higroscopic paper.



**Compatible with mineral oils, MIDEL
And silionic fluids.**

Technical sheet

Density Kg/m ³ :	291
Thickness Micron:	380
Stretched weigh g/m ³ :	70
Crepping %:	1:1,6
Longitudinal stretch %:	80
Mechanical strength KN/m:	4,62
Split stretch %:	92,2
PH value:	7,6



Tlf.: 946 314 289 - | - Fax: 946 313 868
Barrio San Lorenzo s/n 48390 Bedia (Bizkaia)
Mail: apyasa@apyasa.com